

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-095562

(43)Date of publication of application : 08.04.1997

(51)Int.Cl.

C08L 23/00
C08K 5/02
C08K 5/098
C08K 5/13
C08K 5/25
C08K 5/37
H01B 3/44
H01B 7/34

(21)Application number : 07-253502

(71)Applicant : YAZAKI CORP

(22)Date of filing : 29.09.1995

(72)Inventor : HIYOSHI KAZUYASU

(34) FLAME-RETARDANT CROSS-LINKABLE POLYOLEFIN COMPOSITION AND FLAME-RETARDANT ELECTRIC WIRE**(57)Abstract:**

PROBLEM TO BE SOLVED: To obtain a flame-retardant cross-linkable polyolefin compsn. which is excellent in flame retardance and thermal aging properties and is useful esp. as an electrical insulating material and to obtain a flame-retardant electric wire having characteristics described above.

SOLUTION: This compsn. comprises 100 pts.wt. polyolefin, 5-30 pts.wt. chlorinated paraffin, 1-15 pts.wt. Ca-Zn stabilizer, and an antioxidant component comprising 0.1-15 pts.wt. hindered phenol antioxidant, 0.1-5 pts.wt. bis[2-methyl-4-[3-n-alkyl(12-14C)thiopropionyloxy]-5-tert-butylphenyl]sulfide, and 0.1-5 pts.wt. decamethylenedicarboxylic acid disalicyloylhydrazide. A flame-retardant electric wire is obtd. by covering a conductor with the compsn. and cross-linking it.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office